

CLAIMS:

1. A multi-piece solid golf ball comprising a solid core and a cover of two inner and outer layers surrounding the core, the outer cover layer having a surface formed with a plurality of dimples, characterized in that
  - a product of the Shore D hardness of said inner cover layer multiplied by the Shore D hardness of said outer cover layer and a proportion  $V_R$  (%) of the total of the volumes of dimple spaces each defined below a plane circumscribed by the dimple edge to the overall volume of a phantom sphere given on the assumption that the golf ball surface is free of dimples satisfy any one of the following combinations (1) to (5):
    - (1) the product of Shore D hardnesses of inner and outer cover layers: 1,500 to less than 2,000  
 $V_R$ : 0.8 to 1.1%
    - (2) the product of Shore D hardnesses of inner and outer cover layers: 2,000 to less than 2,500  
 $V_R$ : 0.75 to 1.05%
    - (3) the product of Shore D hardnesses of inner and outer cover layers: 2,500 to less than 3,000  
 $V_R$ : .0.7 to 1%
    - (4) the product of Shore D hardnesses of inner and outer cover layers: 3,000 to less than 3,500  
 $V_R$ : 0.65 to 0.95%
    - (5) the product of Shore D hardnesses of inner and outer cover layers: 3,500 to 4,000  
 $V_R$ : 0.6 to 0.9%,
- and said dimples include at least three types of dimples which are different in at least one of a diameter, a depth, and a value  $V_0$  which is the volume of one dimple space defined below a plane circumscribed by the dimple edge divided by the volume of a cylinder whose bottom is the plane and whose height is the maximum depth of the dimple from the bottom.

2. The multi-piece solid golf ball of claim 1 wherein the solid core has a distortion of 2.6 to 6.5 mm under an applied load of 100 kg.

- 5 3. The multi-piece solid golf ball of claim 1 or 2 wherein both the hardnesses of the inner and outer cover layers are up to 63 in Shore D hardness.